

DRUCKFESTIGKEITEN ÜBERSICHT

Informativ



DER FLACHDACHSPEZIALIST

Produkt	N/mm ²	KN/m ²	t/m ²	kPA	E-Modul N/mm ²
EPS-W 15	0,01	10	1	10	4
EPS-W 20	0,02	20	2	20	5
EPS-W 25	0,04	40	4	40	6
EPS-W 30	0,05	50	5	50	8
XPS - G 30	0,11	110	11	110	12
XPS - G 50	0,18	180	18	180	20
XPS - G 70	0,25	250	25	250	23
XPS - G 30 R	0,08	80	8	80	12

Druckspannungen bei 2 % Stauchung

